

FLAMMABILITY TEST REPORT

Report No.: LEHTX00674684 **Date Received:** 14/03/13 **Date Tested:** 20/03/13 **Date Issued:** 20/03/13

Company Name & Address: SUPERLON BALTIC UAB
PRAMONES 3B
PANEVEZYS
LT-35100
LITHUANIA

Contact Name: DARIUS

Sample Details

Order No.: Not stated
Quality: PU CMHR Foam
Colour: Greyish
Supplier: Superlon Baltic UAB
Intended Use: Furniture
Retailer: Not stated
Sample Description: Grey coloured polyurethane foam

Test Method	Pre Treatment	Flammability Performance Requirements	Result
BS 5852: Part 2: 1982, Ignition source 5 (Crib 5).	None	As Schedule 1 Part 1 (Ignition test for polyurethane foam in slab or cushion form) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended).	PASS



ANDREW HALLETT
(Flammability Technician)

DEAN MCCABE
(Flammability Technician)

SIMON CHEE
(Operations Manager)

FLAMMABILITY TEST REPORT

Filling Specification

Filling Type: Polyurethane foam
Density / Hardness: Not stated / Not stated
Cover Fabric: Standard test fabric as detailed in Schedule 1 Part 1 of The Furniture (Fire) (Safety) Regulations 1988 (as amended).

Conditioning

Prior to Testing: At least 72 hours in ambient indoor conditions, then at least 16 hours in an atmosphere having a temperature of 20±5°C and a relative humidity of 50±20%
At Time of Testing: Temperature between 15°C & 30°C. Relative humidity between 20% & 70%

Test Results

"The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test; they are not intended as a means of assessing the fully potential fire hazard of the materials in use."

Pass / Fail Criteria	Initial test		Repeat test	
Progressive smouldering failure				
Externally detectable amounts of smoke, heat or glowing 60 min after crib ignition	No		No	
Escalating smouldering behaviour rendered the test unsafe to continue and required forcible extinction	No		No	
Smouldering essentially consumed the test specimen within the duration of the test	No		No	
Flaming failure				
The test specimen continued to flame for more than 10 minutes after the ignition of the crib	No		No	
Escalating combustion behaviour rendered the test unsafe to continue and required forcible extinction	No		No	
Flaming essentially consumed the test specimen within the duration of the test	No		No	
Final examination				
Progressive smouldering was observed when the sample was dismantled	No		No	
Comments				
Time to extinction of flames after crib ignition	3 Minutes 46 Seconds		3 Minutes 32 Seconds	
Time to extinction of glowing after crib ignition	Due to the position of the crib within the test specimen it was not possible to see when glowing ceased		Due to the position of the crib within the test specimen it was not possible to see when glowing ceased	
Time to extinction of smoke after crib ignition	Due to the amount of smoke in the test enclosure it was not possible to see when smoking ceased		Due to the amount of smoke in the test enclosure it was not possible to see when smoking ceased	
Maximum extent of damage to back (mm) Length / Width	400	140	400	137
Maximum extent of damage to base (mm) Length / Width	94	132	95	130
The resultant mass loss exceeded 60g	No (23 g)		No (23 g)	
Test Result	PASS		PASS	

Conclusions

The sample tested meets the requirements of Schedule 1 Part 1 (Ignition test for polyurethane foam in slab or cushion form) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended). **PASS.**

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.